



1501 West 178th Street | Gardena, California 90248  
 310-767-7812 | 800-359-5679 | fax: 310-767-7836 | info@matsui-color.com | www.matsui-color.com

## Fastness Properties of 301 Neo Pigments

Fastness Identity	light resistance		water resistance	dry clean inability 0.5%		heat resistance		D.S conc. resistance
	5%	1%		mineral spirit	P.C.E	5%	1%	
Neo Yellow M3G	7	6	5	5	4	5	5	4-5
Neo Gold Yellow MFR	8	7	5	5	5	5	5	4-5
Neo Orange MGD	4-5	3-4	5	5	4-5	5	5	4
Neo Red MGD	6-7	5	5	5	4-5	5	4-5	2-3
Neo Red MFB	6	4-5	5	5	4-5	5	4-5	3-4
Neo Rose MB	4-5	4	5	5	5	5	4-5	3-4
Neo Pink MB	8	7-8	5	5	5	5	5	5
Neo Violet MFB	8	7-8	5	5	5	5	5	4-5
Neo Navy Blue MB	8	8	5	5	5	5	4-5	5
Neo Blue MB	8	7-8	5	5	4-5	5	5	5
Neo Blue MG	8	7-8	5	5	5	5	5	5
Neo Green MB	8	7	5	5	5	5	5	2B
Neo Black MK	8	8	5	5	5	5	5	5

### Test Method

Light resistance: Fade-o-Mater 20hrs (JIS L-0842)	8(excellent)→1(weak)
Water resistance: 40°C, 4hrs (JIS L-0846)	5(excellent)→1(weak)
Dry Clean inability: Mineral Spirit & P.C.E. (JIS L-0861)	5(excellent)→1(weak)
Heat resistance: 180°C x 30sec. (JIS L-0850)	5(excellent)→1(weak)
Chemical resistance: D.S conc. baking at 140°C x 5min.	5(excellent)→1(weak)